

# Product Bulletin

## **GF® 666 Eco Floor R9 MATT LAMINATE /**

### **CLEAR PERMANENT ADHESIVE**

GF® 666 is a 90µ matt, monomeric Anti-Slip PVC laminate with a very fine Embossing. The Film is Coated with a Waterbased permanent clear pressure sensitive adhesive on a siliconised kraft liner. This Film has an R9 anti Slip and B1 Fire Certification.

<b>Application:</b>	Short to medium term floor applications	
<b>Thickness</b>	Film	90 mic
	Liner	135 g/m <sup>2</sup>
	(Thickness variance +/- 10%)	
<b>Dimensional Stability</b>	Excellent	
<b>Temperature Ranges</b>	Minimum application temperature	> 10°C
	Service temperature:	-20°C to +70 °C
<b>Adhesion:</b>	15N/25mm – FINAT TM 1, after 24 hours, adhered to stainless steel	
<b>Dimensional stability MD:</b>	≤ 0,5mm- FINAT 14	
<b>Dimensional stability CD:</b>	≤ 0,5mm- FINAT 14	
<b>Tensile Strength:</b>	> 24N/mm <sup>2</sup> - DIN EN ISO 527-1	
<b>Elongation at break:</b>	> 160% - DIN EN ISO 527-1	
<b>Durability:</b>	Up to 2-3 years **	
<b>Usage:</b>	Short to medium floor applications	
<b>Printing:</b>	For laminating solvent, eco-solvent and latex prints.	
<b>Fire rating:</b>	Self-extinguishing, adhered to stainless steel.	
<b>Shelf life at 23°C / 50% moisture:</b>	2 years *	

<b>Product Codes</b>	<b>E666-41 x 50m roll</b>
	<b>E666-54 x 50m roll</b>
	<b>E666-60 x 50m roll</b>

<b>Recommendations</b>	Please ensure the print is perfectly dry before laminating. We suggest to let the material dry for at least 48 hours after printing.
------------------------	---



**General**  
FORMULATIONS

*Manufacturers of Pressure Sensitive Films*

309 S. Union • P.O. Box 158 • Sparta, Michigan 49345 • (616) 887-7387 • (800)253-3664 • FAX (616)887-0537

Web Site:

[www.generalformulations.com](http://www.generalformulations.com) • e-mail: [info@generalformulations.com](mailto:info@generalformulations.com)

We believe the information on this product to be accurate. However, since we cannot anticipate or control the conditions under which this information or our products may be used, we cannot guarantee results obtained through their use. Tests of our products should be made by users to determine the suitability of these products for a specific purpose. The products are sold without warranty, either express or implied. The purchaser should refer to General Formulations, Inc's Price List for Terms and Conditions or Sale, Including Disclaimer of Warranties and Limitation of Liability